International Journal of
Science, Architecture, Technology and Environment

Toward Ultra-Light and High-Efficiency Wind Turbine Blades: Advances in Carbon Fibre Engineering

Pelumi Peter Aluko-0lokun[1*]

[1]*Electrical/Electronics Engieering Department, Sheffield Hallam University, Sheffield, United kingdom*

[*]*Corresponding author*

DOI: https://doi.org/10.63680/ijsate1025007.014

Abstract

The utilisation of carbon fibre in wind turbine technology marks a significant advancement in the pursuit of renewable energy. Renowned for its exceptional strength, stiffness, and fatigue resistance, carbon fibre addresses critical performance limitations associated with traditional materials like glass fibre. This article explores its role in improving turbine efficiency, extending blade lifespans, and reducing maintenance costs, with a particular focus on its potential application in innovative single-blade wind turbines. While single-blade turbines offer advantages such as reduced material use and visual impact, they also face challenges, including unproven reliability and higher failure risks. The high production cost and environmental impact of carbon fibre further complicate its widespread adoption. Computational simulations and life cycle assessments highlight the trade-offs between performance and sustainability, underscoring the need for advanced manufacturing methods, green practices, and experimental validation. By addressing these challenges, carbon fibre can unlock transformative opportunities in wind energy, supporting the development of more efficient and sustainable renewable energy systems. This paper provides insights into material selection, design optimisation, and future research directions essential for advancing wind turbine technology.

Keywords: Carbon Fibre, Wind Turbine Technology, Wind Turbine Designs, Single-Blade Turbines, Sustainable Renewable Energy

1. Introduction

Material innovations are pivotal in enhancing wind turbine performance and efficiency. With the emergence of the potential use of single-blade wind turbines, researchers have been intensively exploring designs and materials that can address challenges related to stability and structural stress distribution [7]. Among these materials, carbon fibre has emerged as a game-changer due to its remarkable mechanical qualities, such as high strength, stiffness, and fatigue resistance, offering unparalleled advantages over traditional materials like glass fibre. A transformative development in renewable energy, carbon fibre wind turbine technology promises to enhance the efficiency, longevity, and sustainability of wind turbine systems [6]. By leveraging the exceptional mechanical properties of carbon fibre composites, wind turbine blades can overcome the

limitations of conventional designs, paving the way for a more sustainable energy future.




Figure 1. Typical carbon-fibre blade
Source: [4].

The excellent strength-to-weight ratio of carbon fibre enables the production of lightweight yet durable turbine blades. This attribute significantly reduces blade weight, enhancing overall turbine efficiency and lowering mechanical stress on critical components [11]. Moreover, the reduced weight contributes to lower transportation and installation costs, improving the cost-effectiveness of wind turbine systems. As the industry continues to innovate, carbon fibre's role in wind energy technology is set to expand, driving advancements in renewable energy solutions.

1. Applications in Wind Turbines

The adoption of carbon fibre in wind turbine technology is gaining momentum, particularly in the development of both traditional three-blade turbines and innovative single-blade designs. Computational models and simulations consistently demonstrate carbon fibre's ability to improve structural stability and energy efficiency. Compared to glass fibre alternatives, carbon fibre blades exhibit significantly reduced stress and deformation, making them a superior choice for long-term reliability and performance.

1.1 Traditional Three-Blade Turbines

Extensive research has established the advantages of carbon fibre in traditional three-blade turbine designs. Key benefits include reduced weight, enhanced fatigue resistance, and improved aerodynamic performance, which collectively lead to higher energy output and lower operational costs [12]. By minimising deflection under load, carbon fibre also ensures greater structural integrity, even under harsh environmental conditions.

1.2 Single-Blade Turbines

The exploration of single-blade wind turbines, while less prevalent, represents an exciting frontier in renewable energy technology. Single-blade designs, such as the Darrieus turbines patented by Georges Jean Marie Darrieus in the 1930s, offer distinctive advantages, including omnidirectional rotation and potential efficiency gains at low wind speeds. However, these designs have historically faced technical challenges,

particularly in maintaining stability and managing structural stress distribution [7].




Figure 2: Geometry of Blade generated in Solidworks

Carbon fibre's exceptional mechanical properties, including its high strength, stiffness, and fatigue resistance, position it as a transformative material for addressing these challenges. Its lightweight nature allows for the creation of single-blade turbine designs that maintain structural stability without sacrificing aerodynamic efficiency [8].

1.3 Aerodynamic Innovations and Computational Simulations

In addition to material advancements, researchers are actively exploring innovative aerodynamic designs to optimise single-blade turbines. Computational fluid dynamics (CFD) simulations have been instrumental in evaluating blade shapes, pitch angles, and aerofoil profiles to maximise energy capture. These simulations have provided critical insights into the development of efficient and stable carbon fibre single-blade wind turbines [10].

2. Advantages of Carbon Fibre

1 The remarkable fatigue resistance and corrosion resistance qualities of carbon fibre significantly extend the useful life of wind turbine blades. This leads to less downtime and reduced maintenance, thereby increasing turbine availability and boosting energy output [1]. By prolonging the service life of wind turbines, carbon fibre blades enhance their economic viability.

2 The use of carbon fibre in traditional three-blade wind turbine designs showcase advantages such as improved energy capture and reduced blade deflections [5].

3 Carbon fibre blades offer superior stiffness, vibration resistance, and fatigue performance compared to glass fibre blades. Finite element analysis (FEA) results indicate enhanced structural integrity, minimising deflection under operational loads.




Figure 3: Total Deformation; Carbon fibre

4 Computational fluid dynamics (CFD) simulations highlight carbon fibre's ability to maintain optimal pitch angles, increasing aerodynamic efficiency and maximising power output at target wind speeds.
5 Although carbon fibre blades are significantly more expensive than glass fibre blades (£22,093 vs. £1,347 per blade) due to energy-intensive production methods, maintenance costs for single-blade turbines remain competitive. However, the high initial capital outlay challenges financial feasibility. Single-blade turbines currently yield a negative net present value (£25,947) compared to £74,947 for three-blade designs.
6 Single-blade turbines offer reduced visual and noise impact, but they face unproven reliability and higher failure risks. Enhancements in fault tolerance and redundancy, such as passive load relief mechanisms, are recommended to improve dependability.
7 Tailoring carbon fibre resin systems and volume fractions can improve blade quality. Real-world testing is crucial for validating computational models and optimising designs. Achieving economic viability will require value engineering, material substitution, and production optimisation.
8 Despite the environmental and economic challenges, carbon fibre offers long-term sustainability benefits through weight reduction, enhanced performance, and reduced resource consumption.

3. Challenges and Future Considerations

1 Economic Barriers: Despite its numerous benefits, carbon fibre faces significant economic challenges, particularly in single-blade wind turbine applications. The high cost of raw materials and energy-intensive production techniques makes carbon fibre blades considerably more expensive than their glass fibre counterparts [3]. This cost disparity poses a major hurdle for widespread adoption, especially in large-scale commercial projects.
2 Manufacturing Challenges: Ensuring consistent quality and dependability in the production of carbon fibre blades is critical. Current manufacturing methods require improvements to minimise defects and guarantee structural reliability. Advanced automation and precision control techniques could help address these issues, reducing costs and improving scalability.
3 Structural and Dynamic Validation: A thorough analysis and experimental validation of the structural response and dynamic behaviour of single-blade wind turbines are imperative. This includes studying how turbines handle wind turbulence, cyclic loading, and resonance phenomena. Computational simulations must be supplemented with real-world testing to ensure accuracy and reliability in diverse operating conditions [2].
4 Quality Control: Maintaining high standards of quality control during blade production is essential to avoid defects that could compromise turbine safety and performance. Advanced inspection technologies, such as ultrasonic testing and thermography, should be integrated into the manufacturing process to ensure defect-free products.
5 Environmental Concerns: While carbon fibre contributes to long-term sustainability through improved turbine performance, its production has a substantial environmental footprint. Efforts to recycle carbon fibre and adopt greener manufacturing practices are critical to reducing this impact.
6 Financial Viability: Large-scale adoption of carbon fibre technology in wind turbines faces financial challenges due to high initial capital investments. Strategies like value engineering, material substitution, and production optimisation must be implemented to enhance cost-efficiency [9].
7 Unproven Reliability in Single-Blade Designs: Single-blade wind turbines, despite their potential advantages, face unproven reliability and higher failure risks compared to traditional designs. Fault

tolerance mechanisms, such as passive load relief systems, should be developed to improve the dependability of single-blade configurations.


8 **Need for Experimental Validation**: While computational models offer valuable insights, real-world testing remains essential to validate design assumptions and optimise turbine performance. Extensive field trials under varying environmental conditions will provide critical data to refine both materials and designs.

Addressing these challenges is pivotal for realising the full potential of carbon fibre in wind turbine applications, particularly in innovative designs like single-blade turbines. By overcoming these obstacles, carbon fibre technology can significantly contribute to the advancement of renewable energy systems.

4. Comparative Analysis

Another potential material is glass fibre. However, finite element analysis (FEA) and life cycle assessments (LCA) underscore carbon fibre's advantages over glass fibre in terms of performance, albeit at higher environmental and economic costs. Long-term benefits, including lower operational costs and increased efficiency, often outweigh these initial drawbacks.

Figure 4: mode shapes of Carbon fiber vs. Glass fiber



4.1. Carbon Fibre vs. Glass Fibre (Single-Blade)

Life cycle assessments reveal that carbon fibre blades have a notably greater carbon footprint and energy consumption compared to glass fibre blades. The carbon footprint of carbon fibre blades is approximately 28,000 kilograms of CO2 equivalent emissions—double that of glass fibre blades at 14,000 kilograms of CO2e. Similarly, the total energy consumption for carbon fibre blades is 480,000 MJ, quadrupling the 160,000 MJ required for glass fibre blades.

The higher environmental impact of carbon fibre production is attributed to its energy-intensive manufacturing processes. Producing high-strength aligned carbon fibres requires high-temperature pyrolysis, followed by energy-intensive oxidation and carbonisation steps. Conversely, glass fibre production involves lower-temperature melting processes, leading to reduced embedded energy.

Table 1: Carbon Fiber Vs. Glass Fiber (Single Blade)

LCA Metric	**Carbon Fiber Blade**	**Glass Fiber Blade**
Carbon Footprint (CO_2e)	28,000 kg	14,000 kg
Total Energy Consumption	480,000 MJ	160,000 MJ
Air Acidification (SO_2e)	54 kg	60 kg
Water Eutrophication Impact	Higher	Lower
Energy-Intensive Processes	High-temp pyrolysis, oxidation	Lower-temp melting
Electricity Source Sensitivity	Affects eutrophication and emissions	Affects SO_2 via fossil fuel use
LCA Metric	Carbon Fiber Blade	Glass Fiber Blade
Carbon Footprint (CO_2e)	28,000 kg	14,000 kg
Total Energy Consumption	480,000 MJ	160,000 MJ
Air Acidification (SO_2e)	54 kg	60 kg
Water Eutrophication Impact	Higher	Lower
Energy-Intensive Processes	High-temp pyrolysis, oxidation	Lower-temp melting
Electricity Source Sensitivity	Affects eutrophication and emissions	Affects SO_2 via fossil fuel use

Carbon fibre also outperforms glass fibre in certain environmental metrics. For instance, carbon fibre blades exhibit lower sulphur dioxide (SO2) equivalent emissions—54 kilograms compared to 60 kilograms for glass fibre blades. This is primarily due to differences in upstream electrical grid emissions, as glass fibre production relies more heavily on fossil fuel-based energy sources. However, carbon fibre blades perform worse in terms of water eutrophication, emitting more nutrients during their production processes. These emissions result

from higher electricity demands, which increase air pollutants and nutrient-rich wastewater discharges, ultimately degrading water quality.

5. Conclusion

The integration of carbon fibre technology in wind turbine design is reshaping the renewable energy landscape by addressing critical challenges in efficiency, durability, and performance. Its superior mechanical properties, including high strength-to-weight ratio, stiffness, and fatigue resistance, have enabled the development of lightweight, durable turbine blades that outperform conventional materials like glass fibre. These advancements result in reduced maintenance requirements, longer operational lifespans, and enhanced energy capture, contributing to improved economic viability over time.

Single-blade wind turbines represent an innovative application of carbon fibre, offering unique benefits such as reduced visual impact, noise levels, and material usage. However, these designs face significant hurdles, including higher initial costs, unproven reliability, and the need for rigorous structural and aerodynamic validation under varied operational conditions. Additionally, the environmental footprint of carbon fibre production raises sustainability concerns, emphasising the necessity of green manufacturing practices and recycling initiatives.

Future breakthroughs in material science, manufacturing technologies, and computational modelling will be pivotal in addressing these challenges. Real-world testing and cost-effective production methods must complement computational simulations to ensure the reliability and affordability of carbon fibre wind turbine technology. By overcoming these barriers, carbon fibre can drive the development of innovative wind energy systems, accelerating the global transition to renewable energy.

Declaration of Conflicting Interests

The authors declare no potential conflicts of interest with respect to the research, authorship and publication of this article.

Funding

The author received no financial support for the research, authorship and publication of this article.

References

[1] U. Baader, M. Depenbrock, G. Gierse: Direct Self Control (DSC) of Inverter Fed Induction Machine: A Basis for Speed Control without Speed Measurement, IEEE Transaction on Industry Applications, Vol. 28, No. 3, May/June 1992, pp. 581 – 588.

[2] Doagou‐Rad, S., Mishnaevsky, L., & Bech, J. I. (2020). Leading edge erosion of wind turbine blades: Multiaxial critical plane fatigue model of coating degradation under random liquid impacts. Wind

Energy, 23(8), 1752-1766.

[3] Etemaddar, M., Blanke, M., Gao, Z., & Moan, T. (2014). Response analysis and comparison of a spar-type floating offshore wind turbine and an onshore wind turbine under blade pitch controller faults. Wind Energy, 19(1), 35-50.

[4] Golkarnarenji, G., Naebe, M., Badii, K., Milani, A., Jazar, R., & Khayyam, H. (2018, March 5). Production of Low Cost Carbon-Fibre through Energy Optimization of Stabilization Process. Materials, 11(3), 385. https://doi.org/10.3390/ma11030385

[5] Aluko-Olokun, P. P. (2024) Life Cycle and Performance Assessment of Carbon Fibre in Single-Blade Wind Turbines International Research Journal of Modernization in Engineering Technology and Science (IRJMETS) 06(12), 2065-2074 DOI: https://www.doi.org/10.56726/IRJMETS65302.

[6] Katsaprakakis, D., Papadakis, N., & Ntintakis, I. (2021). A comprehensive analysis of wind turbine blade damage. Energies, 14(18), 5974. https://doi.org/10.3390/en14185974

[7] Lim, D. W., Mantell, S. C., & Seiler, P. J. (2016, September 9). Wireless monitoring algorithm for wind turbine blades using Piezo-electric energy harvesters. Wind Energy, 20(3), 551–565. https://doi.org/10.1002/we.2023

[8] Moghadassian, B., & Sharma, A. (2020, April). Designing wind turbine rotor blades to enhance energy capture in turbine arrays. Renewable Energy, 148, 651–664. https://doi.org/10.1016/j.renene.2019.10.153

[9] Martinez-Campos, A. F. (2017, July 1). Mechanical Design of a Darrieus Wind Turbine. Workrooms Journal, 1(5). https://doi.org/10.15592/workrooms.2017.0006

[10] Rani, M., Choudhary, P., Krishnan, V., & Zafar, S. (2021, June). A review on recycling and reuse methods for carbon fibre/glass fibre composites waste from wind turbine blades. Composites Part B: Engineering, 215, 108768. https://doi.org/10.1016/j.compositesb.2021.108768

[11] Skovajsa, M., Sedlacek, F., & Mrazek, M. (2020, September 7). Design of Multi-Part Mould for Production of a Medium-Large Carbon Fibre Component. Manufacturing Technology, 20(3), 378–384. https://doi.org/10.21062/mft.2020.055

[12] Viswanathan, P., Prabu, T., Sivasubramaniam, S., & Rudramoorthy, R. (2016, December 26). Aerodynamic Performance Evaluation Of Humpback Whale Inspired Wind Turbine Blade Using Cfd. Advances and Applications in Fluid Mechanics, 19(4), 837–849. https://doi.org/10.17654/fm019040837

[13] Aluko-Olokun, P. P. (2024) Comparative analysis of carbon fibre and glass fibre in blade design World Journal of Advanced Research and Reviews 24(03), 1930-1940 https://doi.org/10.30574/wjarr.2024.24.3.3902.

[14] Yi, G., Zhou, H., Wang, Y., Wu, J., & Wu, J. (2021). Scheme optimization for a turbine blade under multiple working conditions based on the entropy weight vague set. Mechanical Sciences, 12(1), 615-624.

[15] Zheng, T., Zhao, C., & He, J. (2023). Research on fatigue performance of offshore wind turbine blade with basalt fibre bionic plate. Structures, 47, 466-481.